


PRIMA


BOHEMIA COLLECTION

CONSTRUCTION STRUCTURE STRUKTUR STRUCTUUR	Tufting 5/16" loop pile Tufté 5/16" loop pile Getuftet 5/16" loop pile Getuft 5/16" loop pile	FASTNESS TO LIGHT SOLIDITÉ A LA LUMIÈRE LICHTECHTHEIT LICHTECHTHEID	EN ISO 105-B02 ≥ 5-6
PILE MATERIAL COMPOSITION DU VELOURS POLMATERIAL POOLMATERIAAL	100% PP	COLOUR FASTNESS TO WATER SOLIDITÉ À L'EAU WASSERECHTHEIT WATERECHTHEID	EN ISO 105-E01 ≥ 4-5
SECONDARY BACKING DOSSIER RÜCKEN TAPIJTRUG	Texflor® back	FIRE RESISTANCE COMPORTEMENT AU FEU BRENNVERHALTEN BRANDGEDRAG	EN 13501-1 E _{FL} -s1
PILE WEIGHT POIDS DU VELOURS POLEINSATZGEWICHT POOLGEWICHT	± 610 gr/m ²	WIDTH LARGEUR BREITE BREEDTE	EN ISO 3018 ca. 400,500 cm
TOTAL WEIGHT POIDS TOTAL GESAMTGEWICHT TOTAAL GEWICHT	± 1.535 gr/m ²		
PILE THICKNESS EPAISSEUR DU VELOURS POLDICKE POOLDIKTE	± 6 mm		
TOTAL THICKNESS EPAISSEUR TOTALE GESAMTDICKE TOTALE DIKTE	± 8 mm		
TUFT DENSITY NOMBRE DE POINTS NOPPENZAHL AANTAL PUNTEN	± 43.750/m ²		
PRODIS / GUT	8DFDFFE1		
CLASSIFICATION CLASSEMENT KLASSIFIKATION CLASSIFICATIE	EN 1307 22 - LC1		



ITC CO BV
Kanegemstraat 15, B-8700 Tielt
itc-carpets.com



EN 14041
CE
12
ITC CO BV Kanegemstraat 15 - BE 8700 Tielt
DOP: 1010#BA0AEL
Textile Floor Covering EN 1307

my.itc-carpets.com