

Tip proces fabricatie Crosetare 1/10" fir buclat

Antistatic permanent ISO 6356
< 2 kV

Tip material/compozitie 100% PA 6 IMPREL

Evaluarea zgomotului de impact ISO 140-8
24 dB ΔLw

Suport principal non woven PP

Absorbtia sunetului ISO 354
0.15 α_w

Suport secundar Action Back

Rezistenta termica ISO 8302
0.08 m² K/W

Greutate fir Ca. 700 gr/m²

Rezistenta culorii la lumina ISO 105-B02
≥ 5-6

Greutate totala Ca. 1.780 gr/m²

Rezistenta culorii la apa EN ISO 105-E01
≥ 4-5

Inaltime fir Ca. 3.5 mm

Rezistenta la foc EN 13501-1
Cfl-s1 (if glued)

Inaltime totala Ca. 6.1 mm



Rezistenta la frecare EN ISO 105-X12
≥ 4

Densitate crosetare Ca. 234.000/m²

Densitate fir Ca. 0.149 g/cm³

Clasa de trafic EN 1307
33 - Lc2

Rezi. la scaunul cu rotile EN 985
A: intensive use



irom®



arc edition
performance flooring